



ONAFHANKELIJK



LABORATORIUM

Onderzoek en
keuring van
coatings en
bouwmaterialen

Product- en
corrosietests

REPORT

Testing of Transozinc Epoxy Primer
and Transpoxy Glascote
according to Norsok Standard M-501, Rev. 4 system 7

Haarlem, 25 February 2004
RB/MH

Principal Transocean Coatings
Prins Hendrikkade 12 C
3071 KB ROTTERDAM
Attn. Mr. K. Zaal

Order number 310.128

Report number LB04-0187-RAP

COT bv
Zijlweg 340, Haarlem
Postbus 98
2050 AB Overveen
T 023-5319544
F 023-5277229
E info@cot-nl.com
I www.cot-nl.com

Copy Right This report contains 6 numbered pages and is property of COT BV (Netherlands). No part of this report may be copied, distributed, inserted in any text document, or reproduced in any other way or published, without written permission of COT BV (Netherlands). This report is not transferable to any person or body, serves only to take cognisable and gives in no way the rights on this report, neither can lay a claim to any in this report discussed product or method. Use of information from this report is not permitted without written permission of COT BV. When not agreed in the by COT BV provided order confirmation, our Rules of Service are applicable.



ING Bank 690189354
Postbank 326437
KvK Haarlem 34069959



CONTENTS

INTRODUCTION	3
2. GENERAL DATA	3
3. SUBSTRATE	3
4. PAINT APPLICATION AND CURING	3
5. CYCLIC EXPOSURE TEST	4
6. OVERCOATABLE WITHOUT MECHANICAL TREATMENT	4
7. ADHESION TEST - ISO 4624	4
8. CATHODIC DISBONDING TEST - ASTM G8	4
9. REQUIREMENTS	5
10. RESULTS	5
10.1 Adhesion without testing	5
10.2 Cyclic Exposure Test	5
10.3 Cathodic Disbonding Test	6
11 SUMMARY OF TEST RESULTS	6



1. INTRODUCTION

By order of Transocean Coatings in Rotterdam, Holland, Centrum voor Onderzoek en Technisch advies (COT BV) has carried out tests according to Norsok Standard M-501, Rev. 4, system 7. The order has been confirmed in our fax dated 24th April 2003 with reference LB03-0315-FAX by Mr. M. Walrave.

2. GENERAL DATA

Coat	Product name	Colour	Batch number	COT sample number
1	Transozinc Epoxy primer	grey	--	23-04-03/516
2	Transpoxy Glascote	red		23-04-03/513

3. SUBSTRATE

Mild steel panels, thickness 5 mm, blast cleaned to surface preparation grade SA2½ with titanium cast-steel alloy grit, size 0.4 - 1.1 mm.

Roughness: Ra : 9 - 13 micrometres
Rz : 55 - 65 micrometres
Rmax : 70 - 75 micrometres

Maximum content of soluble impurities	Less than the conductivity of 20 mg/m ² NaCl
Cyclic Test panels	Dimensions 75 x 150 mm
Cathodic Disbondment Test panels	Dimensions 100 x 300 mm

4. PAINT APPLICATION AND CURING

The coatings have been sprayed according to the recommendations of the manufacturer

Dry film thickness: Transozinc Epoxy primer : 60 micrometres
Transpoxy Glascote : 400 micrometres

After 3 weeks curing at 23 ± 2°C and 50 ± 5% R.H. the dry film thickness of the paint system have been measured on each panel, after which the tests have been started.



5. CYCLIC EXPOSURE TEST

The fully cured coating system has been scribed horizontal down to bare metal. The scratch line is 2 mm wide and 50 mm long. The system has been exposed to the following cycle:

- 72 hours Salt Spray Test, according to ISO 7253 with synthetic seawater in accordance with ASTM D 1141
- 16 hours Drying in air
- 80 hours UV-A 340 nm weatherometer in accordance with ASTM G 53 (4 hours UV-light at 60°C / 4 hours condensation at 50°C)

The total exposure time is 4200 hours

6. OVERCOATABLE WITHOUT MECHANICAL TREATMENT

After 4200 hours of cyclic testing the system has been coated with one coat Transpoxy Masterbond without mechanical treatment.

After 7 days the adhesion has been determined according to ISO 4624.

7. ADHESION TEST - ISO 4624

The adhesion of the fully cured coating system has been determined by a pneumatic adhesion tester in accordance with ISO 4624. The coating surface and the dolly have been sanded lightly and the epoxy adhesive has been applied. After curing of the adhesive and prior to testing the coating and the adhesive have been scratched around the dolly down to the bare metal. Three trials have been done and the average will be reported. An average of at least 5 MPa shall be acceptable.

8. CATHODIC DISBONDING TEST - ASTM G8

Cathodic disbonding has been determined according to ASTM G8. After 30 days exposure time the maximum disbonding will be less than 10 mm.



9. REQUIREMENTS

Before and after exposure to the specified time, the test panels shall comply with the following requirements:

Method		Requirements
ISO 4628-2	Blistering	0
ISO 4628-3	Rusting	Ri 0
ISO 4628-4	Cracking	0
ISO 4628-5	Flaking	0
ISO 4624	Adhesion	Min 5.0 MPa, max 50 % reduction from original value

Corrosion of the substrate from the scratch shall not exceed 3.0 millimetres.

10. RESULTS

10.1 Adhesion without testing

The average adhesion value is 11.6 ± 5.1 MPa

10.2 Cyclic Exposure Test

Exposure Time: 4200 hours

	Panel 1	Panel 2	Panel 3
Dry film thickness (μm)	441 ± 7	426 ± 15	459 ± 41
ISO 4628-2 Blistering	0	0	0
ISO 4628-3 Rusting	0	0	0
ISO 4628-4 Cracking	0	0	0
ISO 4628-6 Chalking	0	0	0
ISO 4624 Adhesion (MPa)	10.3 ± 1.9	15.9 ± 7.7	8.5 ± 3.1
Corrosion creep according to Rev. 4 (mm)	0.1	0.0	0.0

Adhesion according to ISO 4624 after recoating with one coat of Transpoxy Masterbond after 4200 hours cyclic testing.

1. 15.2 ± 2.6 MPa
2. 14.5 ± 0.8 MPa
3. 15.4 ± 2.3 MPa

10.3 Cathodic Disbonding Test

Maximum disbonding panel 1: 5 mm
Maximum disbonding panel 2: 11 mm
Maximum disbonding panel 3: 9 mm

11. SUMMARY OF TEST RESULTS

Test	Requirement	Result	Pass/Fail
Cyclic exposure test	Max. 3.0 mm creep	2x < 0.1	
Cathodic disbonding	Max. 10 mm disbonding	2x max.9 mm	
Adhesion	At least 5 MPa	11.6 MPa	
Adhesion after cyclic test	< 50% loss of adhesion	≥ 8.5 MPa	
Overcoatability after cyclic test	< 50% loss of adhesion	≥ 14.5 MPa	Pass

CENTRUM VOOR ONDERZOEK
EN TECHNISCH ADVIES (COT)



J.R.S. Brakenhoff
Section Manager Coatings



Ing. M. Walrave
Projectmanager Laboratory